

Electronics

Tweezers

710 Full Plastic Tweezers



Fine paddle tips

A 4 1/2" 115 mm

B 0.03" 7.7 mm

C 0.02" 0.5 mm



710.CF Fine paddle tips; black ESD Carbofib (CF)

General notes

- **PA66/CF30** polyamide 66 reinforced with 30 wt% carbon fibre
- heat stabilized
- very high rigidity, excellent tensile and flexural strength, fatigue and creep resistance
- low friction, self lubricating properties, excellent wear and abrasion resistance
- good heat capability

- good chemical resistance (oils, grease, fuels, non polar solvents); not resistant to strong acids, alkalis and hot water or steam
- ESD safe material, (avoid powder attraction, sparks generation, ignition sources).
- very low coefficient of linear thermal expansion
- typical applications include handling of sensitive components and devices (electronic components, micro-mechanical parts, glass and ceramic substrates, capillary, etc.)

Mechanical propeties

Flexural modulus +23°C:	17000 MPa	ASTM D 790
Flexural modulus +60°C:	12000 MPa	ASTM D 790
Flexural modulus +90°C:	9800 MPa	ASTM D 790
Flexural modulus +120°C	8000 MPa	ASTM D 790
Tensile strength +23°C	210 MPa	ISO 527
Tensile strength +60°C	159 MPa	ISO 527
Tensile strength +90°C	134 MPa	ISO 527
Tensile strength +120°C	117 MPa	ISO 527
Rockwell hardness M:	>100	ASTM D 785
Izod-Impact strength (notched) +23°C	70 J/m	ASTM D 785
Charpy-Impact strength (unnotched)	30 kJ/m ²	DIN 53453

Thermal properties

Temp. of defl. uner load (1.80 MPa):	256 °C	ASTM D648
Temp. of defl. uner load (0.45 MPa):	260 °C	ASTM D648
Vicat softening temperature (50 °C/h 50N)	254 °C	ISO 306
Coef. of lin.therm expansion, normal:	2.80 E-5/°C	ASTM D 696
Continuous Use Temperature	130 °C	20'000 h
Short Time Temperature	190 °C	

Electrical properties

Surface resistivity	10 ² Ohm	100V
Comparative tracking index:	<100 Volts	IEC 112
Decay time:	< 0.1 sec	1000-10 V

Other properties

Density	1.28 g/ccm	ISO 1183
Water absorption in water 23°C (24h)	0.60 %	ISo 62

© 2013 IDEAL-TEK SA

Credits